



Technical Datasheet

PP A0665

Description & Typical Applications

PP A0665 is an off grade of (Petrochemicals Postindustrial)

It is HOMOPOLYMER PP - it is ideal for rigid injection molding (general purpose applications.)

Processing Conditions

Temperature °C 200-230

Polymer Properties

PROPERTIES (Range)	TYPICAL VALUES	UNITS	TEST METHOD
@ 190 °C and 2.16 kg	10 - 13	g/10min	ASTM D1238
Density	903- 907	kg/m ³	ASTM D1505
Ash Content	0	%	ASTM D2584

